



p: 318-220-0995
 e: info@beauxartsconservation.com
 w: www.beauxartsconservation.com

Date: 11/27/2020	Invoice: 2020.2
Client:	
Address:	
Phone:	
Email:	

Object	Condition and Treatment Report
--------	--------------------------------

2020.2 - Federal Style Mirror

The mirror is in overall good condition. The silvering to the back of the mirror is intact. The frame and mirror are dirty. There are several losses throughout the gilt frame and several stress fractures. The proper right wingtip of the eagle is missing up to 4". There are paint losses to several of the balls to the interior of the round frame. There is a missing section to a floret at the bottom of the frame, an area to the left of the floret, and a leaf to the proper right with loss of gesso. The cardboard backing to the mirror has broken into three pieces.

The frame was dusted with a soft brush, then wiped with a soft cloth damp with distilled water. Small areas were cleaned with cotton swabs and distilled water. Stress fractures and cracks were secured with a 50% solution of Acryloid B-72 in acetone. The exposed areas of gesso were secured with one coat of 15% solution of Acryloid B-72 in acetone. The wingtip and missing area to the left of the floret were fabricated with Miliput and shaped with cotton swabs and distilled water. Other losses were filled with Flugger acrylic spackle. The fills were refined with cabinet paper or cotton swabs dampened with distilled water. The losses and fabrications were inpainted using a mixture of Golden Acrylic Matte Medium, Golden Acrylic Paint, and mica powders to match the surrounding areas.

Before



After



Before



After

